

# SCG Thin Wall Flame Retarded Tubing



## APPLICATIONS:

Light duty wire harnessing for electrical and electronic applications. Provides electrical insulation and protection for in-line components. Bundles wires and cables. Used as strain relief for electrical wire connection. Bus-bar insulation for switchgear. Color coding for wires, cables, terminals and components.

## GENERAL PROPERTIES OF PRODUCT:

- Shrink ratio 2:1
- Flame retarded and self-extinguishing
- For Electrical Insulation up to 600 volts
- Resistance to chemical, copper corrosion and fungus
- UV stabilized
- Standard Colors: Black, White, Yellow, Red, Blue, Green and Clear
- Meet ROHS Compliance

## SPECIFICATIONS:

**Spec:** MIL-1-23053/5 Class 2 & 3, UL224 125 deg. C VW1, CSA C22.2 No. 198.1 OFT

Part Number/Size	Internal Diameter (mm)		Recovered Wall Thickness (mm)	Packing Configurations		
	Supplied	Recovered		Spools Meters/Spool	Cut Lengths 1.2 meter/box	Dispenser Box Meters/box
SCG 1.0/0.5	1.0 mm	0.5 mm	0.36 mm	200 m		
SCG 1.5/0.75	1.5 mm	0.75 mm	0.36 mm	200 m	1000	20 m
SCG 2.0/1.0	2.0 mm	1.0 mm	0.44 mm	200 m		
SCG 2.5/1.2	2.5 mm	1.2 mm	0.44 mm	200 m	600	20 m
SCG 3.0/1.5	3.0 mm	1.5 mm	0.44 mm	200 m		
SCG 3.5/1.7	3.5 mm	1.7 mm	0.44 mm	200 m	500	20 m
SCG.04/2.0	4.0mm	2.0 mm	0.44 mm	200 m		
SCG 5.0/2.5	5.0 mm	2.5 mm	0.56 mm	100 m	250	10 m
SCG 6.0/3.0	6.0 mm	3.0 mm	0.56 mm	100 m		
SCG 7.0/3.5	7.0 mm	3.5 mm	0.56 mm	50 m	200	10 m
SCG 8.0/4.0	8.0 mm	4.0 mm	0.56 mm	50 m		
SCG 9.0/4.5	9.0 mm	4.5 mm	0.56 mm	50 m		
SCG 10.0/5.0	10.0 mm	5.0 mm	0.56 mm	50 m	100	10 m
SCG 12.0/6.0	12.0 mm	6.0 mm	0.56 mm	50 m		
SCG 13.0/6.5	13.0 mm	6.5 mm	0.69 mm	50 m	120	5 m
SCG 14.0/7.0	14.0 mm	7.0 mm	0.69 mm	50 m		
SCG 16.0/8.0	16.0 mm	8.0 mm	0.69 mm	50 m		
SCG 18.0/9.0	18.0 mm	9.0 mm	0.78 mm	50 m		
SCG 20.0/10.0	20.0 mm	10.0 mm	0.78 mm	50 m	65	5 m
SCG 22.0/11.0	22.0 mm	11.0 mm	0.78 mm	50 m		
SCG 25.0/12.5	25.0 mm	12.5 mm	0.86 mm	50 m	40	5 m
SCG 30.0/15.0	30.0 mm	15.0 mm	0.86 mm	50 m		
SCG 40.0/20.0	40.0 mm	20.0 mm	0.96 mm	25 m	20	
SCG 50.0/25.0	50.0 mm	25.0 mm	0.96 mm	25 m	15	
SCG 76.0/38.0	76.0 mm	38.0 mm	1.27 mm	25 m	10	
SCG 100/50.0	100.0 mm	50.0 mm	1.40 mm	25 m	5	

## Product Technical Data

PROPERTIES	TEST METHOD	TYPICAL VALUE
Tensile Strength	ASTM-D-638	16 N/mm <sup>2</sup>
Water Absorption	ASTM-D-570	.15% Max.
Elongation	ASTM-D-638	300%
Low Temperature Flexibility	ASTM-D-2671	-55 °C
Specific Gravity	ASTM-D-792	1.4
Longitudinal Change	ASTM-D-638	>3%
Flammability	UL224-VW1	Pass
<b>Thermal:</b>		
Operating Temperature	IEC216	-55°C to +125°C
Heat Shock@ 250 °C 4 hrs		No dripping, cracking or flowing
<b>Chemical:</b>		
Fungus Resistance	MIL-1-7444	Inert
Copper Corrosion	ASTM D 2671 B	XX
Chemical Resistance		XX
<b>Electrical :</b>		
Dielectric Strength	ASTM-D-2671	>20kV / mm
Dielectric Constant	ASTM-D-150	3.0 Max.
Volume Resistance	ASTM-D-257	10 <sup>16</sup> Ohm/cm

### Flamability:

Not Self Extinguishing	1
Flame Retarded	2
Self Extinguishing	3

### Chemical Resistance and Copper Corrosion:

X	Satisfactory
XX	Good
XXX	Excellent

Disclaimer: The company reserves the rights to make changes to the products and their specifications with prior notice. The above information given corresponds to our actual knowledge and are according our knowledge is rendered correct and reliable. But they do not represent binding properties. Customers and end-users have to decide autonomously about application in the provided range. Under no circumstances is Radiform Insulation Industries Pte Ltd liable for any eventual, indirect or consequential damages arising from the sales, resales, transfer, use or misuse of the product. Our liabilities are limited to only in replacing products due to manufacturing defects.